



APRINTA PRO



## PrintaMent PLA

	Printing T	Bed Temperature	Printing Speed	Fan Speed 2nd Layer	Flow Rate
BCN3D Sigma	195°-220°C	off*   >65°C	Up to 70 mm/s	100%	100%
Ultimaker 2	195°-220°C	off*   >65°C	Up to 80 mm/s	100%	100%
Ultimaker 2+	195°-220°C	off*   >65°C	Up to 80 mm/s	100%	100%
Ultimaker 3	195°-220°C	off*   >65°C	Up to 80 mm/s	100%	100%
BQ Wittbox 1	190°-215°C	n.A.*	Up to 60 mm/s	100%	100%
BQ Wittbox 2	190°-215°C	n.A.*	Up to 60 mm/s	100%	100%
BQ Hephestos	190°-215°C	n.A.*	Up to 60 mm/s	100%	100%
Prusa i3	190°-215°C	off*   >65°C	Up to 60 mm/s	100%	100%
Prusa i3 MK2	190°-215°C	off*   >65°C	Up to 60 mm/s	100%	100%

\*coated with PrintaFix